

ORAJET® 3551RA HIGH PERFORMANCE CALENDERED PVC DIGITAL MEDIA WITH RAPIDAIR® TECHNOLOGY

Technical Datasheet
10/19
Page 1 of 2

Description

2.75-mil, high performance calendered PVC film in white with a gloss surface and RapidAir® Technology



Release Liner

88# PE-coated silicone paper featuring advanced air release technology to facilitate quicker, easier application

Adhesive

Grey, solvent-based repositionable, permanent adhesive that, with heat, can be removed with little or no adhesive residue for up to four years.

Area of Use

For medium- to long-term outdoor general signage and vehicle graphics requiring limited conformability

Technical Data

Thickness (without liner and adhesive)	2.75-mil
Dimensional Stability (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, <.008"
Temperature Resistance	Adhered to aluminum, -58°F to +194°F, no variation
Fire Behavior (DIN 75200) Fire Rating	Adhered to steel, self-extinguishing ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 4.1 lb/in
Tensile Strength (DIN EN ISO 527)	Along: Min. 19 MPa Across: Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	Along: Min. 130% Across: Min. 150%
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	7 years (unprinted)
Minimum Application Temperature	46°F
Available Lengths Available Widths	150' (50-yard) 30", 50", 54", 60"
Recommended Laminates	ORAGUARD® Series 215, 290, 290GF, 293, 297GF
Print Compatibility	Latex, Solvent, Eco-Solvent, UV Curable

For best results, utilize ORAFOL ICC profiles available at www.orafolamericas.com and allow solvent-based inks to dry for at least 24 hours (48-72 hours preferred) at 70°F before cutting the graphic to the ink or applying a laminate.

Note

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Films with structured surface are naturally more sensitive than the unstructured. Accordingly, these films are to be treated carefully both in processing and in cleaning. Impurities affect the appearance of structured films and require more frequent cleaning. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.



Equipos y Materiales para Impresión Digital de Gran Formato

Tel. 01 (55) 5617 2599 / 01 800 71 85 600

www.sagaró.com.mx

contacto@sagaró.com.mx

Sucursales: CDMX Sur, CDMX Centro, Tlalnepantla EdoMex, Puebla, Monterrey, Guadalajara, Torreón, Querétaro, León, Veracruz, Mérida.

ORAJET® 3551RA HIGH PERFORMANCE CALENDERED PVC DIGITAL MEDIA WITH *RAPIDAIR*® TECHNOLOGY

Technical Datasheet
10/19
Page 2 of 2

IMPORTANT NOTICE

All ORAJET® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAJET® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAJET® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use.

All specifications are subject to change without prior notice.

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm.



Equipos y Materiales para Impresión Digital de Gran Formato

Tel. 01 (55) 5617 2599 / 01 800 71 85 600

www.sagaró.com.mx

contacto@sagaró.com.mx

Sucursales: CDMX Sur, CDMX Centro, Tlalnepantla EdoMex, Puebla, Monterrey, Guadalajara, Torreón, Querétaro, León, Veracruz, Mérida.